

# TRUPON<sup>®</sup> AMC

## Fatliquor for softy leather

Basis:	sulphited and phosphatised raw materials
Appearance:	beige, pasty
Charge:	anionic
Active matter:	approx. 40 %
pH value (1 : 10):	approx. 8
Acid stability:	excellent
Salt stability:	excellent
Chrome stability:	excellent
Light fastness:	excellent
Heat yellowing:	good

### **Properties:**

**TRUPON AMC** is ideally suited for fatliquoring of all types of softy leathers including furniture leather where its use will provide a light fluffy handle, a smooth grain characteristic and an even level dying.

**TRUPON AMC** exhibits on suede leathers excellent softness together with outstanding sheen and lustre.

**TRUPON AMC** is designed as main fatliquor, but it can be also applied during chrome tannage.

**TRUPON AMC** will enhance the colour value of dyed leather.

### **Application:**

**TRUPON AMC** can be used alone or in combination with other anionic fatliquors.

**TRUPON AMC** should be prepared for use by adding it to a minimum of five times its own volume of water at 50 °C whilst stirring.

Quantities to be used will depend upon the processing stage and the degree of softness required, but will normally vary between 6 -12 %, based on shaved weight.

**Safety and storage:**

When handling **TRUPON AMC**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPON AMC** can be stored for up to 12 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON AMC** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.