

# TRUPOTAN<sup>®</sup> BIO-08P

## modified biopolymer

Basis:	modified biopolymer with low molecular weight
Appearance:	light brown powder
Charge:	amphoteric
pH value(1 : 10):	approx. 7,5
Light fastness:	excellent
Heat yellowing:	excellent

### Properties:

**TRUPOTAN BIO-08P** is a natural-based biopolymer suitable for the production of all types of leather.

**TRUPOTAN BIO-08P** is free of formaldehyde.

**TRUPOTAN BIO-08P** imparts to the leather a good fullness and a mellow handle.

**TRUPOTAN BIO-08P** produces leather with a firm grain and a silky touch.

**TRUPOTAN BIO-08P** improves the dye intensity and levelness on chrome free leathers as well as on chrome leathers.

For the production of splits or other suede articles **TRUPOTAN BIO-08P** produces a short and even nap with a very good writing effect.

**TRUPOTAN BIO-08P** has no negative influence on waterproofing articles

### **Application:**

The **TRUPOTAN BIO-08P** can be applied in the retanning process as well as in the dyeing process before fixing with formic acid.

The applied quantity normally lies between 6 – 8 %, based on shaved weight.

### **Safety and storage:**

When handling **TRUPOTAN BIO-08P**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN BIO-08P** can be stored for up to 24 months, if kept in a dry place.