

# TRUPOTAN<sup>®</sup> MAU

## resin syntan

Basis:	condensation resin based on melamine compounds
Appearance:	colourless liquid
Charge:	amphoteric
pH value(1 : 10):	approx. 8
Light fastness:	excellent
Heat yellowing:	good

### **Properties:**

**TRUPOTAN MAU** is a retanning agent, based on melamine resin compounds for application in the retanning for all types of leather.

**TRUPOTAN MAU** brings about an increase in fullness and improves the grain tightness.

**TRUPOTAN MAU** does not bleach the dyeings.

### **Application:**

Between 1 and 2 % **TRUPOTAN MAU** may be applied in the pickle process to improve the grain tightness and fullness.

In the neutralisation between 2 and 4 % **TRUPOTAN MAU** may be applied together with other neutralising syntans, for example **TRUPOTAN NS**.

In the retanning between 3 and 6 % **TRUPOTAN MAU** may be applied and this will help to improve the exhaustion and fixing of other anionic retanning agents.

**TRUPOTAN MAU** may also be applied to help fixation of the top dyeings which will also improve their fastness properties.

### **Safety and storage:**

When handling **TRUPOTAN MAU**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN MAU** can be stored for up to 12 months, if temperatures below 5 °C and above 35 °C can be avoided. Drums should be kept sealed until use. Under less than ideal storage conditions it is possible that **TRUPOTAN MAU** will exhibit an increase in viscosity and a reduction of its water solubility.

Should this condition arise, the product can be corrected by adding a small quantity of diluted organic acid, i. e. formic acid to **TRUPOTAN MAU** before use.