

TRUPOTAN[®] MON

basifying agent

Appearance:	beige powder
-------------	--------------

Properties:

TRUPOTAN MON is a safety basifying agent which provides a uniform basification without significant pH jumps.

TRUPOTAN MON improves chrome exhaustion and chrome fixation and provides even chrome distribution.

Application:

TRUPOTAN MON is added to the chrome liquor after the chrome has largely penetrated the skin.

In the case of thin-split pelts **TRUPOTAN MON** might be added in one rate undissolved after 30 - 60 mins.

For thicker split or non-split pelts **TRUPOTAN MON** should be added after 2 - 3 hours, if possible in two rates of same quantity within a period of 30 - 60 mins.

After addition of **TRUPOTAN MON** the tanning process should be continued for approx. 8 hours so that a complete reaction can be guaranteed. The final temperature for the tanning process should be approx. 40 °C.

The necessary quantity of **TRUPOTAN MON** to be applied varies between 0.35 and 0.55 % (calculated on pelt weight) and depends upon thickness of pelt, pickle pH-value and chromium offer.

If temperature is above 30 °C when adding **TRUPOTAN MON**, the rise of pH is faster.

Safety and storage:

When handling **TRUPOTAN MON**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets. **TRUPOTAN MON** can be stored for up to 18 months, if kept in a dry place.