

TRUPOTAN[®] MOW

basifying agent

Appearance:	white powder
-------------	--------------

Properties:

TRUPOTAN MOW is a safety basifying agent which provides a uniform basification without significant pH jumps.

TRUPOTAN MOW improves chrome exhaustion and chrome fixation and provides even chrome distribution.

Application:

TRUPOTAN MOW is added to the chrome liquor after the chrome has largely penetrated the skin.

In the case of thin-split pelts **TRUPOTAN MOW** might be added in one rate undissolved after 30 - 60 mins.

For thicker split or non-split pelts **TRUPOTAN MOW** should be added after 2 - 3 hours, if possible in two rates of same quantity within a period of 30 - 60 mins.

After addition of **TRUPOTAN MOW** the tanning process should be continued for approx. 8 hours so that a complete reaction can be guaranteed. The final temperature for the tanning process should be approx. 40 °C.

The necessary quantity of **TRUPOTAN MOW** to be applied varies between 0.35 and 0.55 % (calculated on pelt weight) and depends upon thickness of pelt, pickle pH-value and chromium offer.

If temperature is above 30 °C when adding **TRUPOTAN MOW**, the rise of pH is faster.

Safety and storage:

When handling **TRUPOTAN MOW**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN MOW can be stored for up to 24 months, if kept in a dry place.