

TRUPON[®] EZR

fatliquor for softy leather

| | |
|--------------------|---|
| Basis: | sulphated and sulphited natural and synthetic raw materials |
| Appearance: | red brown pourable oil |
| Charge: | anionic |
| Active matter: | approx. 70 % |
| pH value (1 : 10): | approx. 7.5 |
| Acid stability: | good |
| Salt stability: | excellent |
| Chrome stability | excellent |
| Light fastness: | excellent |
| Heat yellowing: | medium |

Properties:

TRUPON EZR is a highly stable anionic fatliquor which can be utilised to good effect in many types of leather, from shoe upper to garment nappa.

TRUPON EZR imparts to the leather a full round handle with excellent softness.

TRUPON EZR due to its inbuilt safety factors is an ideal choice for all leathers where quality coupled with ease of use is a prerequisite.

Application:

TRUPON EZR can be used at levels of between 0.5 - 2.0 % (based on pickled or shaved weight) in both chrome tanning and retanning baths as well as in compact retanning systems where high levels of electrolytes may preclude the use of other less stable fatliquors.

Safety and storage:

When handling TRUPON EZR, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPON EZR can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature TRUPON EZR may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.