

# TRUPOSYL<sup>®</sup> TBD

## fatliquor on polymer basis

Basis:	special combination of lubricating polymers
Appearance:	opalescent paste
Charge:	anionic
Active matter:	approx. 60 %
pH value(1 : 10):	approx. 8
Acid stability:	good
Salt stability:	good
Chrome stability:	good
Light fastness:	excellent
Heat yellowing:	good

### **Properties:**

Leathers prepared with **TRUPOSYL TBD** have a tight smooth grain and significantly improved fullness.

**TRUPOSYL TBD** has an excellent stability to electrolytes and can therefore be applied as a pre-fatliquor in the chrome retan float, producing a good fullness and spring in the final leather.

For waterproof leather the **TRUPOSYL TBD** is intended to be used only as a pre-fatliquor, followed by normal processing with **TRUPOSIST<sup>®</sup> D**.

Leathers treated with **TRUPOSYL TBD** demonstrate level and brilliant dyeing properties that are particularly useful for suede and nubuck leather production.

### **Application:**

**TRUPOSYL TBD** can be used for all types of leather and in any combination with other anionic fatliquors.

**TRUPOSYL TBD** can be utilised to good effect in compact processes where its use will help to simplify and reduce the number of products utilised.

Quantities to be applied with vary between 3 - 10 %, based upon shaved weight, depending upon the type of leather required.

### **Safety and storage:**

When handling **TRUPOSYL TBD** normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOSYL TBD** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOSYL TBD** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.