

# TRUPOTAN<sup>®</sup> GD

## replacement syntan

Basis:	condensation of aryl sulphonic acid and hydroxyl aryl sulphone
Appearance:	yellowish powder
Charge:	anionic
pH value(1 : 10):	approx. 3.5
Light fastness:	excellent
Heat yellowing:	excellent

### **Properties:**

**TRUPOTAN GD** is a replacement syntan with universal application in the retanning/bleaching of wet blue and for application together with vegetable tannins in low float tanning systems.

**TRUPOTAN GD** produces a white, mellow and tight grained leather with good fullness. The grain is especially fine and very suitable for milling.

**TRUPOTAN GD** may be applied in the retannage together with other syntans and resins to improve the penetration and dispersion

### **Application:**

**TRUPOTAN GD** can be added directly as powder, or dissolved, to the tanning/retanning drum.

When applied in vegetable tanning **TRUPOTAN GD** bleaches the colour of the leather and accelerates the penetration of tannins.

### **Retannage of wet blue:**

For the retannage of wet blue we recommend that 4 - 8 % **TRUPOTAN GD**, based upon shaved weight, be offered. Due to excellent fastness and tanning properties **TRUPOTAN GD** is very suitable for the production of chrome-free upholstery

### **Safety and storage:**

When handling **TRUPOTAN GD**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN GD** can be stored for up to 24 months, if kept in a dry place.