

# TRUPOTAN<sup>®</sup> PT

## pre-tanning agent

|                    |                        |
|--------------------|------------------------|
| Appearance:        | brown liquid           |
| Basis:             | modified polyaldehydes |
| pH value (1 : 10): | approx. 4              |

### **Properties:**

**TRUPOTAN PT** is a pre-tanning agent used for stabilising the collagen structure.

**TRUPOTAN PT** when used in the tanning process, shrinkage temperatures in excess of 70 °C can be achieved.

**TRUPOTAN PT** guarantees an efficient samming of the hides and skins, thus allowing for a more accurate shaving.

**TRUPOTAN PT** offers excellent softness and fullness, coupled with uniform dyeing.

**TRUPOTAN PT** improves the penetration and distribution of vegetable and synthetic tanning agents in the subsequent main tannage.

**TRUPOTAN PT** is ideally suited for the manufacture of all types of chrome-free leathers and as pre-tanning agent prior to thickness levelling in order that chrome shavings can be avoided.

### **Application:**

3 - 4 % **TRUPOTAN PT**, based on pelt weight, are added undiluted at the end of the pickle process. After a running time of 8 - 10 hrs. the pH value will have to be adjusted to 4.0 – 4.4 by adding sodium bicarbonate. An additional syntan is not required as **TRUPOTAN PT** ensures a sufficient samming effect.

**TRUPOTAN PT** should be used in combination with a fungicide, in order to avoid mould formation.

For the production of upholstery leather we would recommend to use a fatliquor in the pickle e. g. **TRUPON<sup>®</sup> PEM**.

**Safety and storage:**

When handling **TRUPOTAN PT**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN PT** can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided.