

# TRUPOTAN<sup>®</sup> QL

## auxiliary syntan

Basis:	naphthalene compounds
Appearance:	dark brown liquid
Charge:	anionic
Active matter:	approx. 50 %
pH value(1 : 10):	approx. 3.5
Light fastness:	excellent
Heat yellowing:	good

### **Properties:**

**TRUPOTAN QL** is a pre- and retanning syntan intended mainly for vegetable tanned leather, based on naphthalene.

**TRUPOTAN QL** eases the penetration of the vegetable tannins in the tanning and retanning processes.

### **Application:**

In the pretanning between 5 and 8 % **TRUPOTAN QL** is applied, calculated on pelt weight.

In the retanning between 2 and 6 % **TRUPOTAN QL** is applied, based on shaved weight. In the retannage the **TRUPOTAN QL** will accelerate the penetration of anionic dyes, syntans and polymers.

During the retannage of sheep, goat and calf skins between 2 and 6 % **TRUPOTAN QL** together with the chrome in the rechrome will improve the fineness and tightness of the grain.

### **Safety and storage:**

When handling **TRUPOTAN QL**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN QL** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN QL** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.