

# TRUPOTAN<sup>®</sup> R83

## polymer retanning agent

Basis:	polyacrylic acids
Appearance:	viscous liquid
Charge:	anionic
Active matter:	approx. 33 %
pH value(1 : 10):	approx. 3.5
Light fastness:	excellent
Heat yellowing:	excellent

### **Properties:**

**TRUPOTAN R83** is a retanning agent based on acrylic acids for the retanning of all types of leathers.

**TRUPOTAN R83** produces leathers with excellent fullness and softness together with a tight, fine grain.

**TRUPOTAN R83** improves the buffing properties.

**TRUPOTAN R83** has bleaching properties and is very suitable for the production of white and pastel dyed leathers.

### **Application:**

In the retanning between 2 and 4 % **TRUPOTAN R83** is recommended, calculated on shaved weight. Optimal fullness and effect with **TRUPOTAN R83** is achieved when added after running with neutralisation syntans.

Increasing the float temperature or the addition of formic acid increases the uptake and exhaustion of **TRUPOTAN R83**.

### **Safety and storage:**

When handling **TRUPOTAN R83**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN R83** can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN R83** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.