

# TRUPOTAN<sup>®</sup> USN

## masking basifying agent

Appearance:	beige powder
-------------	--------------

### Properties:

**TRUPOTAN USN** is a safety basifying agent with well-balanced masking properties specially for un-split pelts.

A major advantage of **TRUPOTAN USN** is the uniform and slow pH increase during basification. No risk of a sudden pH increase exists.

**TRUPOTAN USN** provides a very even chrome distribution.

**TRUPOTAN USN** improves chrome exhaustion and fixation.

**TRUPOTAN USN** contributes to an excellent full and fine grain leather. The colour of the wet blue is very clear and level.

### Application:

**TRUPOTAN USN** is added to the chrome liquor after the chrome has largely penetrated the pelt.

Due to the slow pH increase **TRUPOTAN USN** can be added in one rate.

After addition of **TRUPOTAN USN** the tanning process should be continued for approx. 9 hours so that a complete reaction can be guaranteed. The final temperature for the tanning process should be approx. 40 °C or higher (50 °C).

The usual quantity of **TRUPOTAN USN** to be applied varies between 0.6 and 1.0 % (calculated on pelt weight) and depends upon thickness of the pelt, pickle pH-value and chromium offer.

**Safety and storage:**

When handling **TRUPOTAN USN**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN USN** can be stored for up to 24 months, if kept in a dry place.