

# TRUPOFIX<sup>®</sup> SA2

## auxiliary agent to avoid chrome VI

Basis:	mixture of organic reducing agents
Appearance:	yellow brown liquid
pH value (1 : 10):	approx. 3

### Properties:

**TRUPOFIX SA2** can prevent the oxidation of chrome III to chrome VI.

**TRUPOFIX SA2** can decrease an existing chrome VI amount.

**TRUPOFIX SA2** has no negative influence on the quality of the final leather. Touch, colour and physical properties remain unchanged.

### Application:

**TRUPOFIX SA2** should be best applied at the end of the dyehouse process in the wash after fixation. We recommend a temperature of 30 °C and a running time of 60 minutes. Quantities to be used will be between 2.0 - 4.0 %, based upon shaved weight.

Moreover it is possible to spray a 40% solution on the flesh side of crust or finished leathers.

### Safety and storage:

When handling **TRUPOFIX SA2**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOFIX SA2** can be stored for up to 12 months, if temperatures below 10 °C and above 40 °C can be avoided.

Drums should be kept tightly closed after using **TRUPOFIX SA2**.