

TRUPOSIST® S-BO

silicone based booster for hydrophobic leathers

Basis:	water emulsifiable functional silicones
Appearance:	pale yellow liquid
Charge:	weakly anionic
pH value(1 : 10):	ca. 8
Acid stability:	low
Salt stability:	low
Light fastness:	excellent
Heat yellowing:	excellent

Properties:

TRUPOSIST S-BO is a custom-designed "booster" ideally suited for use in combination with other **TRUPOSIST** hydrophobic fatliquors where it will greatly enhance their waterproofing properties.

Chrome-tanned leathers which require a high degree of retannage with anionic materials often prove difficult in achieving optimum hydrophobic results. The use of **TRUPOSIST S-BO** will markedly improve the hydrophobic nature of such leathers without detracting from aestetic properties.

In addition, the use of **TRUPOSIST S-BO** will have no adverse effect on the dyeing or finishing properties of the leather.

As a result of the special functional compounds in **TRUPOSIST S-BO** outstanding substantivity and fixation in the leather is assured.

Application:

TRUPOSIST S-BO can be utilized at levels between 1-3 %, based on shaved weight, together with other TRUPOSIST hydrophobic fatliquors such as **TRUPOSIST S-DN** e.g.:

1/2

08/2012

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

4-6% TRUPOSIST S-DN

+

3 – 1 % TRUPOSIST S-BO

The two products should be mixed together prior to emulsification in water at ca. 50 °C. Process temperatures between 45 - 55 °C and running times of between 60 - 120 minutes. will normally suffice to afford even penetration and good exhaustion, acidification of the fatliquoring bath to pH 3.6 - 3.8 with additions of diluted formic acid will assist in fixation and preparation of the leather for after treatment with a suitable mineral tanning material such as 33 % basic chrome powder. In order to enhance water resistance properties and negate grain pebbling and the danger of reduced area yield it is recommended that **TRUPOFIX® WP.** be utilized together with the mineral capping material at a level of approximately 0.3 - 0.4 % together with 3.0 - 4.0 % chrome.

For further details concerning water resistant leather we suggest reference be made to the section ,**HYDROPHOBIC FATLIQUORS AND AUXILIARIES**' contained in our catalogue.

Safety and storage:

When handling **TRUPOSIST S-BO**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOSIST S-BO can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. At temperatures below 15 °C **TRUPOSIST S-BO** may exhibit a marked increase in viscosity. On prolonged storage **TRUPOSIST S-BO** may show some degree of settlement which can be rectified by either warming and/or stirring the products thoroughly before use.