

# TRUPOTAN<sup>®</sup> OXB

## aldehyde tanning agent

Basis:	modified aldehyde compounds
Appearance:	yellowish liquid
Charge:	anionic
pH value (1 : 10):	approx. 10
Light fastness:	excellent
Heat yellowing:	excellent

### **Properties:**

**TRUPOTAN OXB** is an aldehyde tanning agent that can be applied in the pretannage, main tannage or retannage.

**TRUPOTAN OXB** is ideal for the production of small skins.

**TRUPOTAN OXB** increases the shrinkage temperature of pickled pelts.

**TRUPOTAN OXB** applied in the pretannage, brings about a more homogeneous distribution of the natural fats.

**TRUPOTAN OXB** improves the dye properties, especially the dye levelling.

Leathers pretanned with **TRUPOTAN OXB**, demonstrate a pleasant, full, mellow, round handle.

### **Application:**

In the pretannage between 1 and 3 % **TRUPOTAN OXB** will improve the following main tanning agent penetration.

When depickling and degreasing pickled sheepskins between 2 and 4 % **TRUPOTAN OXB** is recommended.

In rechroming between 1 and 3 % **TRUPOTAN OXB** will improve the chromium exhaustion and improve the perspiration and wash fastness properties.

In the retannage of vegetable tanned leathers **TRUPOTAN OXB** can increase the hydrothermal stability.

**Safety and storage:**

When handling **TRUPOTAN OXB**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN OXB** can be stored for up to 12 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN OXB** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.