

# TRUPON<sup>®</sup> V200

## fatliquor for woolskins

Basis:	combination of highly sulphonated long chain synthetic raw materials and nonionic stabilizers
Appearance:	pale coloured pourable oil
Charge:	anionic
Active matter:	approx. 73 %
pH value(1 : 10):	approx. 7
Acid stability:	excellent
Salt stability:	excellent
Chrome stability:	excellent
Light fastness:	good
Heat yellowing:	excellent

### **Properties:**

**TRUPON V200** produces milky emulsions in water which have outstanding resistance to electrolytes and mineral tanning salts.

**TRUPON V200** is specifically designed for use on woolskins and skins particularly where a mending system of paddle tannage is in operation.

**TRUPON V200** due to its make up and outstanding electrolyte stability has a beneficial effect upon the dispersal and re-distribution of natural fat and grease within the pelt. Skins fatliquored with **TRUPON V200** exhibit good softness with a dry fluffy handle and exceptionally clean white wools.

**TRUPON V200** has excellent properties in terms of penetration and exhaustion from long float systems and exhibits good fibre substantivity.

## **Application:**

In chrome and alum tanning baths: 6 - 10 g per litre  
For subsequent packs: 4 - 8 g per litre

In order to achieve optimum results when using **TRUPON V200** in the tanning liquor, we would always recommend that the product be pre-emulsified by adding it to at least 4 times its own volume of water at 40 - 50 °C before adding to the tan liquor.

## **Safety and storage:**

When handling **TRUPON V200**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPON V200** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON V200** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.