

TRUPOTAN[®] QL

auxiliary syntan

| | |
|-------------------|-----------------------|
| Basis: | naphthalene compounds |
| Appearance: | dark brown liquid |
| Charge: | anionic |
| Active matter: | approx. 50 % |
| pH value(1 : 10): | approx. 3.5 |
| Light fastness: | excellent |
| Heat yellowing: | good |

Properties:

TRUPOTAN QL is a pre- and retanning syntan intended mainly for vegetable tanned leather, based on naphthalene.

TRUPOTAN QL eases the penetration of the vegetable tannins in the tanning and retanning processes.

Application:

In the pretanning between 5 and 8 % **TRUPOTAN QL** is applied, calculated on pelt weight.

In the retanning between 2 and 6 % **TRUPOTAN QL** is applied, based on shaved weight. In the retannage the **TRUPOTAN QL** will accelerate the penetration of anionic dyes, syntans and polymers.

During the retannage of sheep, goat and calf skins between 2 and 6 % **TRUPOTAN QL** together with the chrome in the rechrome will improve the fineness and tightness of the grain.

Safety and storage:

When handling **TRUPOTAN QL**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN QL can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN QL** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.