

TRUPON[®] LP2

chrome stable universal fatliquor

| | |
|-------------------|---|
| Basis: | sulphited and sulphated natural and synthetic raw materials |
| Appearance: | yellow brown pourable oil |
| Charge: | anionic |
| Active matter: | approx. 65 % |
| pH value(1 : 10): | approx. 8 |
| Acid stability: | excellent |
| Salt stability: | excellent |
| Chrome stability: | excellent |
| Light fastness: | excellent |
| Heat yellowing: | medium |

Properties:

TRUPON LP2 is a semi synthetic universal fatliquor.

Leathers fatliquored with **TRUPON LP2** possess very good softness and handle coupled with a mellow smooth grain.

TRUPON LP2 can be used at all stages of the leather making process including chrome tanning or retanning as well as in the neutralisation stage where its 'in-built' emulsion stability will allow good penetration of the softening components throughout the cross section of the leather.

Application:

TRUPON LP2 can be used alone or in combination with other anionic fatliquors.

Quantities to be used will depend upon the processing stage and the degree of softness required, but will normally vary between

| | |
|--------------|--|
| 0.5 – 1.5 % | in chrome tannage |
| 1.0 – 2.0 % | in chrome retannage and neutralisation |
| 5.0 – 10.0 % | in main fatliquoring |

Safety and storage:

When handling **TRUPON LP2**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPON LP2 can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON LP2** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.