

# TRUPOSOL® AWL

## fatliquor for automobile and upholstery leather

Basis:	sulphited natural and synthetic fatting substances
Appearance:	red brown oil
Charge:	anionic
Active matter:	approx. 55 %
pH value(1 : 10):	approx. 7.5
Acid stability:	medium
Salt stability:	good
Chrome stability:	medium
Light fastness:	excellent
Heat yellowing:	good

#### **Properties:**

**TRUPOSOL AWL** is a semi synthetic fatliquor specially developed to meet the stringent demands laid down in the production of automobile leather.

**TRUPOSOL AWL** can be utilised to good effect in the fatliquoring of 'chrome free' upholstery and automotive leathers which require good softness coupled with tight grain characteristics.

**TRUPOSOL AWL** exhausts readily from anionic dye baths resulting in low COD levels in waste water. Leathers fatliquored with **TRUPOSOL AWL** exhibit outstanding gravimetric fogging values.

#### **Application:**

**TRUPOSOL AWL** can be used alone or in combination with other **TRUPOSOL** fatliquors. Quantities to be use will depend upon the degree of softness required, but will normally vary between 8 - 16 %, based on shaved weight.

1/2

10/2013

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

### **Safety and storage:**

When handling **TRUPOSOL AWL**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOSOL AWL** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOSOL AWL** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

2/2

10/2013

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.