

# TRUPOTAN<sup>®</sup> RKM

## polymer retanning agent

Basis:	polyacrylic acid compound
Appearance:	viscous liquid
Charge:	anionic
Active matter:	approx. 30 %
pH value(1 : 10):	approx. 7.5
Light fastness:	excellent
Heat yellowing:	excellent

### **Properties:**

**TRUPOTAN RKM** is a polymer retanning agent on the basis of polyacrylic acids intended for the retannage of all types of leather.

**TRUPOTAN RKM** increases the fullness and grain tightness.

**TRUPOTAN RKM** eases the penetration of dyestuffs without reducing the dye intensity.

### **Application:**

**TRUPOTAN RKM** can be applied in the neutralisation process or in the retannage. After neutralisation between 2 and 4 % **TRUPOTAN RKM**, based on shaved weight, can be used to increase the softness and fullness of the leather.

In the retannage between 2 and 6 % **TRUPOTAN RKM** can be applied, based on the shaved weight, to improve the grain tightness.

### **Safety and storage:**

When handling **TRUPOTAN RKM**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN RKM** can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN RKM** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.