

TRUPOTAN[®] RP

polymer retanning agent

Basis:	polyacrylic acids
Appearance:	light viscous liquid
Charge:	anionic
Active matter:	approx. 30 %
pH value(1 : 10):	approx. 6
Light fastness:	excellent
Heat yellowing:	excellent

Properties:

TRUPOTAN RP is a polymer retanning agent based on acrylic acids for the retanning of all types of soft leathers.

TRUPOTAN RP increases the leather fullness.

TRUPOTAN RP produces leathers with a very good softness and a very fine grain.

TRUPOTAN RP produces low density light leathers and improves the milling properties.

Application:

In the retanning between 3 and 6 % **TRUPOTAN RP**, based on shaved weight, is applied.

In the retannage of waterproof leathers between 3 and 6 % **TRUPOTAN RP** improves the fullness and the grain tightness without reducing the effect of the water resistant fatliquors for example **TRUPOSIST[®]**.

Safety and storage:

When handling **TRUPOTAN RP**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN RP can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN RP** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.