

# TRUPOSOL<sup>®</sup> AWL

## fatliquor for automobile and upholstery leather

Basis:	sulphited natural and synthetic fatting substances
Appearance:	red brown oil
Charge:	anionic
Active matter:	approx. 55 %
pH value(1 : 10):	approx. 7.5
Acid stability:	medium
Salt stability:	good
Chrome stability:	medium
Light fastness:	excellent
Heat yellowing:	good

### **Properties:**

**TRUPOSOL AWL** is a semi synthetic fatliquor specially developed to meet the stringent demands laid down in the production of automobile leather.

**TRUPOSOL AWL** can be utilised to good effect in the fatliquoring of 'chrome free' upholstery and automotive leathers which require good softness coupled with tight grain characteristics.

**TRUPOSOL AWL** exhausts readily from anionic dye baths resulting in low COD levels in waste water. Leathers fatliquored with **TRUPOSOL AWL** exhibit outstanding gravimetric fogging values.

### **Application:**

**TRUPOSOL AWL** can be used alone or in combination with other **TRUPOSOL** fatliquors. Quantities to be use will depend upon the degree of softness required, but will normally vary between 8 - 16 %, based on shaved weight.

### **Safety and storage:**

When handling **TRUPOSOL AWL**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOSOL AWL** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOSOL AWL** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.