

# TRUPOTAN<sup>®</sup> RP

## polymer retanning agent

Basis:	polyacrylic acids
Appearance:	light viscous liquid
Charge:	anionic
Active matter:	approx. 30 %
pH value(1 : 10):	approx. 6
Light fastness:	excellent
Heat yellowing:	excellent

### **Properties:**

**TRUPOTAN RP** is a polymer retanning agent based on acrylic acids for the retanning of all types of soft leathers.

**TRUPOTAN RP** increases the leather fullness.

**TRUPOTAN RP** produces leathers with a very good softness and a very fine grain.

**TRUPOTAN RP** produces low density light leathers and improves the milling properties.

### **Application:**

In the retanning between 3 and 6 % **TRUPOTAN RP**, based on shaved weight, is applied.

In the retannage of waterproof leathers between 3 and 6 % **TRUPOTAN RP** improves the fullness and the grain tightness without reducing the effect of the water resistant fatliquors for example **TRUPOSIST<sup>®</sup>**.

### **Safety and storage:**

When handling **TRUPOTAN RP**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN RP** can be stored for up to 24 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN RP** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.