

TRUPOFIN[®] WAX HP-N

hydrophobing pull-up wax

Basis:	hydrophobing waxes and fatty substances
Appearance:	pale coloured waxy substance
Active matter:	100 %
Melting point:	40-45°C

Properties:

TRUPOFIN WAX HP-N has been specifically developed for application by heated rollercoater.

TRUPOFIN WAX HP-N will produce strong pull-up effects of high contrast coupled with a fine waxy handle.

In addition to its aesthetic qualities, leathers treated with **TRUPOFIN WAX HP-N** exhibit a marked degree of water resistance even on material which has not been previously treated with waterproofing fatliquors.

Leathers which have been processed utilising waterproofing materials such as **TRUPOSIST[®] WRM** or the **TRUPOSIST** system will exhibit enhanced water resistance and lower water uptake when treated with **TRUPOFIN WAX HP-N**.

Application:

TRUPOFIN WAX HP-N is best applied in undiluted form at a level of between 10 - 20 g per sqft. and at a temperature of 65 - 85°C.

Extended drying or conditioning of the leathers is not required due to the absence of solvents in the system. A final plating or ironing of the finished leather will ensure good levelling and high gloss.

Safety and storage:

When handling **TRUPOFIN WAX HP-N**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data

sheets.

TRUPOFIN WAX HP-N can be stored for up to 18 months, if temperatures below 5°C and above 40°C can be avoided. On prolonged storage or extremes of temperature **TRUPOFIN WAX HP-N** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

Packaging/Containers:

Drums: 40 kg