

TRUPON® PEW3

lightfast fatliquor for all softy leathers

Basis:	sulphited vegetable oils
Appearance:	yellow brown oil
Charge:	anionic
Active matter:	approx. 65 %
pH value(1 : 10):	approx. 7
Acid stability:	excellent
Salt stability:	excellent
Chrome stability:	excellent
Light fastness:	excellent
Heat yellowing:	medium

Properties:

TRUPON PEW3 is a fatliquor which provides exceptional softening properties on a wide range of leathers.

TRUPON PEW3 can be utilised to advantage in chrome tanning as well as the neutralising stage where it will assist in maintaining the tear strength of the leather.

When used in the main fatliquoring stage **TRUPON PEW3** will produce leather with outstanding softness and lightness coupled with fine mellow grain characteristics.

Application:

TRUPON PEW3 can be used alone or together with other anionic fatliquors where it will assist in stabilising the fatliquoring emulsion thus helping to improve penetration and lightness of the leather.

1/2

09/2013

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

Safety and storage:

When handling **TRUPON PEW3**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPON PEW3 can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON PEW3** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

2/2

09/2013

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.