

# TRUPOTAN<sup>®</sup> US

## masking basifying agent

Appearance:	beige powder
-------------	--------------

### Properties:

**TRUPOTAN US** is a safety basifying agent with well-balanced masking properties specially for un-split pelts.

A major advantage of **TRUPOTAN US** is the uniform and slow pH increase during basification. No risk of a sudden pH increase exists.

**TRUPOTAN US** provides a very even chrome distribution.

**TRUPOTAN US** improves chrome exhaustion and fixation.

**TRUPOTAN US** contributes to an excellent full and fine grain leather. The colour of the wet blue is very clear and level.

### Application:

**TRUPOTAN US** is added to the chrome liquor after the chrome has largely penetrated the pelt. Due to the slow pH increase **TRUPOTAN US** can be added in one rate.

After addition of **TRUPOTAN US** the tanning process should be continued for approx. 9 hours so that a complete reaction can be guaranteed. The final temperature for the tanning process should be approx. 40 °C or higher (50 °C).

The usual quantity of **TRUPOTAN US** to be applied varies between 0.7 and 1.1 % (calculated on pelt weight) and depends upon thickness of the pelt, pickle pH-value and chromium offer.

### Safety and storage:

When handling **TRUPOTAN US**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN US** can be stored for up to 24 months, if kept in a dry place.