

# TRUPOTAN<sup>®</sup> WRT

## auxiliary syntan

Basis:	styrene malein copolymer
Appearance:	viscous liquid
Charge:	anionic
Active matter:	approx. 34 %
pH value (1 : 10):	approx. 8.5
Light fastness:	excellent
Heat yellowing:	excellent

### Properties:

TRUPOTAN WRT is a styrene malein copolymer retanning agent.

TRUPOTAN WRT is suitable for the production of waterproof shoe upper leather.

TRUPOTAN WRT improves greatly the grain tightness.

With TRUPOTAN WRT a leather with good stand, a fine elastic grain and a pleasant handle is produced.

TRUPOTAN WRT supports extraordinarily the properties of the waterproof fatliquors and is very suitable to be used together with a TRUPOSIST<sup>®</sup> -system.

### Application:

In the retanning normally between 3 and 6 % TRUPOTAN WRT, calculated on shaved weight, is utilised. The quantity applied depends on the type of leather and required fullness.

## Safety and storage:

When handling **TRUPOTAN WRT**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

**TRUPOTAN WRT** can be stored for up to 18 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPOTAN WRT** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.