

TRUPOSIST[®] H

hydrophobing agent

Basis:	polymeric, hydrophobing and fattening substances
Appearance:	light yellow, viscous oil
Charge:	anionic
pH value (1 : 10):	approx. 8
Acid stability:	medium
Salt stability:	good
Light fastness:	excellent
Heat yellowing:	excellent

Properties:

TRUPOSIST H is a hydrophobing agent designed for water resistant leathers with the highest demands.

TRUPOSIST H is designed for use on leathers treated with large quantities of anionic syntans, resins and vegetable-based retanning materials.

TRUPOSIST H provides excellent dyeing properties without danger of greasiness, thus making it ideally suited for the production of high quality full grain and nubuck leathers.

TRUPOSIST H exhibits sufficient stability to salts and weakly acidic conditions so it can be used at various stages of processing.

TRUPOSIST H is ideally suited for the production of washable leathers where softness and handle will be retained even after several washing cycles, through to the highest specification water resistant shoe upper leathers.

Leathers treated with **TRUPOSIST H** exhibit a pleasant, full and round handle with extremely high dynamic water resistance.

Application:

TRUPOSIST H can be used alone in the main fatliquoring process, or proportionally at other stages indicated. Quantities to be used will be dependent upon the softness required, but will normally lie between 6 - 10 % based upon shaved weight.

TRUPOSIST H should be added to the drum in pre-emulsified form. Process temperatures between 45 - 55 °C and running times of between 60 - 120 min will assist with the even penetration of the fatliquor.

In order to enhance water resistance properties and negate grain pebbling and the danger of reduced area yield, it is recommended that **TRUPOFIX®WP** be utilized together with the mineral capping material.

For further details concerning water resistant leather we suggest reference be made to the section, "HYDROPHOBIC FATLIQUORS AND AUXILIARIES" contained in the **TRUMPLER** Product Catalogue.

Safety and storage:

When handling **TRUPOSIST H**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOSIST H can be stored for up to 18 months, if temperatures below 5°C and above 40°C are avoided. At temperatures below 15°C **TRUPOSIST H** may exhibit a marked increase in viscosity. On prolonged storage **TRUPOSIST H** may show some degree of settlement which can be rectified by either warming and/or stirring the product thoroughly before use.

Packaging/Containers:

Drums: 115 kg

IBC: 1000 k