

TRUPON[®] AMC

Fatliquor for softy leather

Basis:	sulphited and phosphatised raw materials
Appearance:	beige, pasty
Charge:	anionic
Active matter:	approx. 40 %
pH value (1 : 10):	approx. 8
Acid stability:	excellent
Salt stability:	excellent
Chrome stability:	excellent
Light fastness:	excellent
Heat yellowing:	good

Properties:

TRUPON AMC is ideally suited for fatliquoring of all types of softy leathers including furniture leather where its use will provide a light fluffy handle, a smooth grain characteristic and an even level dyeing.

TRUPON AMC exhibits on suede leathers excellent softness together with outstanding sheen and lustre.

TRUPON AMC is designed as main fatliquor, but it can be also applied during chrome tannage.

TRUPON AMC will enhance the colour value of dyed leather.

Application:

TRUPON AMC can be used alone or in combination with other anionic fatliquors.

TRUPON AMC should be prepared for use by adding it to a minimum of five times its own volume of water at 50 °C whilst stirring.

Quantities to be used will depend upon the processing stage and the degree of softness required, but will normally vary between 6 -12 %, based on shaved weight.

Safety and storage:

When handling **TRUPON AMC**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPON AMC can be stored for up to 12 months, if temperatures below 5 °C and above 40 °C can be avoided. On prolonged storage or extremes of temperature **TRUPON AMC** may exhibit some settlement which can be rectified by either warming and/or stirring the product thoroughly before use.