

TRUPOTAN[®] MAU

resin syntan

| | |
|-------------------|--|
| Basis: | condensation resin based on melamine compounds |
| Appearance: | colourless liquid |
| Charge: | amphoteric |
| pH value(1 : 10): | approx. 8 |
| Light fastness: | excellent |
| Heat yellowing: | good |

Properties:

TRUPOTAN MAU is a retanning agent, based on melamine resin compounds for application in the retanning for all types of leather.

TRUPOTAN MAU brings about an increase in fullness and improves the grain tightness.

TRUPOTAN MAU does not bleach the dyeings.

Application:

Between 1 and 2 % **TRUPOTAN MAU** may be applied in the pickle process to improve the grain tightness and fullness.

In the neutralisation between 2 and 4 % **TRUPOTAN MAU** may be applied together with other neutralising syntans, for example **TRUPOTAN NS**.

In the retanning between 3 and 6 % **TRUPOTAN MAU** may be applied and this will help to improve the exhaustion and fixing of other anionic retanning agents.

TRUPOTAN MAU may also be applied to help fixation of the top dyeings which will also improve their fastness properties.

Safety and storage:

When handling **TRUPOTAN MAU**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN MAU can be stored for up to 12 months, if temperatures below 5 °C and above 35 °C can be avoided. Drums should be kept sealed until use. Under less than ideal storage conditions it is possible that **TRUPOTAN MAU** will exhibit an increase in viscosity and a reduction of its water solubility.

Should this condition arise, the product can be corrected by adding a small quantity of diluted organic acid, i. e. formic acid to **TRUPOTAN MAU** before use.