

TRUPOTAN[®] XP

modified, lightfast aldehydic tanning agent

| | |
|--------------------|-----------------------------|
| Basis: | modified aliphatic aldehyde |
| Appearance: | clear liquid |
| Active matter: | approx. 45% |
| Charge: | neutral |
| pH value (1 : 10): | approx. 6 |
| Lightfastness: | excellent |

Properties:

TRUPOTAN XP is a modified aliphatic aldehydic tanning agent.

TRUPOTAN XP is highly compatible with most chemicals and assists with the even penetration and distribution of tanning and retanning chemicals, fatliquors and dyestuffs.

TRUPOTAN XP improves chrome exhaustion both in tanning and rechroming baths.

TRUPOTAN XP may be utilised in retanning and fatliquoring to improve softness and provide fine, smooth and soft grained leathers.

TRUPOTAN XP enhances dye distribution to provide leathers with even, brilliant shades. Pretanning with **TRUPOTAN XP** helps with the removal and even distribution of natural fats when used with the **TRUMPLER PASTOSOL[®]** series in the aqueous degreasing of sheepskins. **TRUPOTAN XP** may also be used as a pretannage to assist with the penetration and distribution of vegetable tanning agents.

Application:

Quantities to be used will depend upon chemical combinations utilized and the properties required, but will commonly vary between:

TRUPOTAN XP, 1-2% (based on limed weight), may be used prior to the addition of chrome tanning salts

TRUPOTAN XP, 1-4% (based on shaved weight), is recommended for use in rechroming prior

to the addition of chrome tanning salts, neutralisation, retanning, fatliquoring and/or dyeing.

Application (cont...):

Pretanning with **TRUPOTAN XP**:

2-4g/L **TRUPOTAN XP** (based on 8L per skin), is recommended for the pretanning of wool-on sheepskins.

2-4% **TRUPOTAN XP**, is recommended for the pretanning of vegetable tanned leathers (based on limed weight) and sheepskins (based on pickled weight + 50%) before degreasing with appropriate **PASTOSOL®** products

Safety and storage:

When handling **TRUPOTAN XP**, normal safety precautions associated with the handling of chemicals should be observed. For more specific details please refer to our safety data sheets.

TRUPOTAN XP can be stored for up to 24 months, if temperatures below 5 °C and above 40°C can be avoided.

Packaging/Containers:

Drums: 125 kg

IBC: 1100 kg